

PAROC Pro Wired Mat 80

(PAROC Wired Mat 80)



Short Description

Stone wool wired mat. Available also with stainless steel net; code W2 will be added after the product name.

Application

Fire and thermal insulation of cylindrical, conic and level surfaces.

Technical Properties

Nominal Density

80 kg/m³

Maximum Service Temperature

750 °C

PAROC stone wool products are capable of withstanding high temperatures. The binder starts to evaporate when its temperature exceeds approximately 200°C. The insulating properties remain unchanged, but the compressive stress weakens. The softening temperature of stone wool products is over 1000°C.

Dimensions

Width x Length

width x 2000 - 6000 mm

Other Dimensions

Width can be 500, 600, 900 or 1000 mm depending on the supplying factory.

Thickness

30 - 120 mm

Packaging

Plastic Packs on Pallet

Fire Properties

Reaction to Fire, Euroclass

A1

In accordance with

EN 13501-1

Thermal Properties

Thermal Conductivity in 10 °C, λ_{10} 0.035 W/mK

Thermal Conductivity in 50 °C, λ_{50} 0.040 W/mK

Thermal Conductivity in 100 °C, λ_{100} 0.047 W/mK

Thermal Conductivity in 150 °C, λ_{150} 0.056 W/mK

Thermal Conductivity in 200 °C, λ_{200} 0.067 W/mK

Thermal Conductivity in 300 °C, λ_{300} 0.093 W/mK

Thermal Conductivity in 400 °C, λ_{400} 0.127 W/mK

Thermal Conductivity in 500 °C, λ_{500} 0.167 W/mK

Values announced by manufacturer.

Moisture Properties

Complies with the requirements set by BS 2972 Part 12.

Other Information

PAROC Wired Mat 80 can be used to satisfy the requirements as given in the tables for insulation thickness in BS5422:2009. Paroc can offer help and assistance to customers to confirm that the insulation systems proposed do in fact, achieve the necessary performance criteria. PAROC Wired Mat 80 conforms to BS3958-3.



PAROC OY AB, P.O. Box 47 (Läkkisepäntie 23), FI-00621 Helsinki Finland, Tel. +358 46 876 8000, Fax +358 46 876 8002, www.paroc.com

The information in this data sheet represents the sole and comprehensive description of the condition of the product and its technical properties. However, the content of this data sheet does not mean granting a commercial guarantee. In so far as the product is used in an area of use which is not provided for in this data sheet, we cannot warrant its suitability for said area of use unless the suitability was expressly confirmed by us upon request. This data sheet replaces all previous ones. As a result of constant further development of our products we reserve the right to make alterations to data sheets. PAROC and red and white stripes are registered trade marks of Paroc Oy Ab. © Paroc Group 2011